


### Elcometer 123 Surface Profile Gauge



Elcometer 123 Surface Profile Gauge

#### At a glance

- Analogue surface profile gauge used to measure surface roughness.
- Place the gauge on the gloss to zero and then measure your surface.

### **Elcometer 123 Surface Profile Gauge**

This is an easy to use gauge that measures the point-to-valley height of a blast cleaned surface.

The average of a series of measurements provides and indication of the surface roughness and allows the surfaces to be compared as blasting proceeds.

- Simple and low cost
- Metric and Imperial Versions

#### **Surface Profile**

The proper and effective preparation of a surface prior to coating is essential. Making sure that the correct roughness – or profile – has been generated is essential.

If the profile is too low, the adhesion of the coating to the surface will be reduced. Too high and there is the danger that the profile peaks will remain uncoated – allowing rust spots to occur.

Can be used in accordance with:		
ASTM D 4417- B	SABS 772	

	Elcometer 123	
	0 - 1000mm	
Range		
	0 – 40 mils	
	2mm	
Scale Resolution		
	0.1 mils	
	105 x 55 x 25mm	
Dimensions (nominal)		
	4.1 x 2.2 x 1"	
	235g	
Weight		
	8oz	
Power	Not Required	
Part Numbers	Metric	E123AM-
	Imperial	E123AE-

# data sheet

#### Related products



Elcometer 223



Elcometer 101/45



Elcometer 122



Elcometer 125



Elcometer 129



Elcometer 127



Elcometer 7060

The Elcometer 223 is a battery operated digital surface profile gauge which measures the peak-to-valley height of a surface in a similar way to the Elcometer 123 analogue equivalent, but with the added benefit of a direct RS232 output for data logging.

Whereas comparators allow the estimation of surface roughness by both touch and sight, the Elcometer 101 estimates the roughness of iron and steel surfaces. Its scale indicates the suitability of the surface for paints, metal coatings and hard metal coatings.

The Elcometer 122 testex tape allows the user to measure the peak-to-valley height of the profile and record it. Testex tape consists of foam with a non-compressible backing. The foam side is rubbed into the surface providing a permanent mould of the profile. The Elcometer 124 Thickness Gauge is then used to measure the peak-to-valley height of the profile formed.

Surface comparators allow the estimation of surface roughness by both touch and sight. These simple roughness gauges consist of 4 blasted profiles of varying roughness and are available either in a grit blasted or a shot blasted version.

Similar to the Elcometer 125, the Elcometer 129 roughness comparators are available in two models: The Elcometer 129 Rubert is available in grit and shot versions whereas the Elcometer 129 Rugotest includes the shot and grit profiles on the same block.

These comparators from Keane-Tator are designed to be used with a magnifier. Consisting of 5 blasted profiles on displayed with the roughness value on each disc. In the middle of the disc there is a hole for the comparison to be undertaken using the magnifier. Sand, shot or grit versions available.

Designed for measurement of machined profiles, these gauges measure the profile by the use of a motorised travel of the sensor which passes over the surface to be tested. A range of different roughness values can be displayed on the LCD.

## Icomete

#### **ENGLAND**

Elcometer Ltd Edge Lane Manchester M43 6BU

Tel: +44 (0)161 371 6000 Fax: +44 (0)161 371 6010 e-mail: sales@elcometer.com www.elcometer.com

Elcometer Inc 1893 Rochester Industrial Drive Rochester Hills Michigan 48309

Tel: +1 248 650 0500 Toll Free: 800 521 0635 Fax: +1 248 650 0501 e-mail: inc@elcometer.com www.elcometer.com

#### **CANADA**

Elcometer Ltd PO Box 622, 401 Ouelette Avenue Windsor, Ontario N9A 6N4

Tel: +1 248 650 0500 Toll Free: 800 521 0635 Fax: +1 248 650 0501 e-mail: ca\_info@elcometer.com www.elcometer.com

#### **ASIA & THE FAR EAST**

Elcometer (Asia) Pte Ltd 896 Dunearn Rd Sime Darby Centre #3-09 Singapore 589472, Republic of Singapore

Tel: +65 6462 2822 Fax: +65 6462 2860 e-mail: asia@elcometer.com www.elcometer.com

#### **BELGIUM**

Elcometer SA Rue Vallée 13 B-4681 Hermalle /s Argenteau

Tel: +32 (0)4 379 96 10 Fax: +32 (0)4 374 06 03 e-mail: be\_info@elcometer.be www.elcometer.be

#### **FRANCE**

Elcometer Sarl 97 Route de Chécy 45430 BOU

Tel: +33 (0)2 38 86 33 44 Fax: +33 (0)2 38 91 37 66 e-mail: fr\_info@elcometer.fr www.elcometer.fr

#### **GFRMANY**

Elcometer Instruments GmbH Ulmer Strasse 68 D-73431 Aalen

Tel: +49 (0)7361 52806 0 Fax: +49 (0)7361 52806 77 e-mail: de info@elcometer.de www.elcometer.de

www.elcometer.com