

Elcometer 5100 Payne Permeability Cups



Elcometer 5100 Payne Permeability Cups

Elcometer 5100 Payne Permeability Cups

Instrument made entirely of anodised aluminium, used to determine the permeability of films of paint, varnish, plastic, cellophane, etc.

The film is gripped between a ring fitted with a seal and the cup, which contains a quantity of water.

The water evaporates and after a certain time the weight loss relative to the film thickness is calculated, indicating the degree of permeability.

Drying Time

When developing a process, it is often important to know the exact time it takes for the coating to dry or cure.

There are many stages to the coating drying time. Once a coating has been applied, the first stage is that the coating levels off under gravity. Once a coating begins to cure, a thin dry film appears on the surface. The coating then continues to dry and finally after a period of time, the coating is totally cured.

But how do you know when a coating is totally dry?

Using the Elcometer Drying Time Recorder, the operator can easily identify each of the stages of the drying process.

At a glance

- Used to determine the permeability of a coating.
- Precision product for reliable results.

Can be used in accordance with:	
ASTM E 96-80	ISO 7783
NF T 30-018	

Model	Description	Area		Part Number
		cm ²	sq. inch	
Elcometer 5100/1	Elcometer 5100 Payne Permeability Cup	10	1.55	K0005100M201
Elcometer 5100/2	Elcometer 5100 Payne Permeability Cup	30	4.65	K0005100M202
Elcometer 5100/3	Elcometer 5100 Payne Permeability Cup	50	7.75	K0005100M203
Accessories	Spare Rubber Seal for Elcometer 5100/1			KT005100P002
	Spare Rubber Seal for Elcometer 5100/2			KT005100P003
	Spare Rubber Seal for Elcometer 5100/3			KT005100P004
Packing List	Elcometer 5100 Payne Permeability Cup, Storage case & Operating instructions			

Related products



Elcometer 7300

A professional high precision stopwatch is required for measuring the flow time of a coating or other product under test with a viscosity cup.

ENGLAND

Elcometer Ltd
Edge Lane
Manchester M43 6BU

Tel: +44 (0)161 371 6000
Fax: +44 (0)161 371 6010
e-mail: sales@elcometer.com
www.elcometer.com

USA

Elcometer Inc
1893 Rochester Industrial Drive
Rochester Hills Michigan 48309

Tel: +1 248 650 0500
Toll Free: 800 521 0635
Fax: +1 248 650 0501
e-mail: inc@elcometer.com
www.elcometer.com

CANADA

Elcometer Ltd
PO Box 622, 401 Ouelette Avenue
Windsor, Ontario N9A 6N4

Tel: +1 248 650 0500
Toll Free: 800 521 0635
Fax: +1 248 650 0501
e-mail: ca_info@elcometer.com
www.elcometer.com

ASIA & THE FAR EAST

Elcometer (Asia) Pte Ltd
896 Dunearn Rd
Sime Darby Centre #3-09
Singapore 589472,
Republic of Singapore

Tel: +65 6462 2822
Fax: +65 6462 2860
e-mail: asia@elcometer.com
www.elcometer.com

BELGIUM

Elcometer SA
Rue Vallée 13
B-4681 Hermalle /s Argenteau

Tel: +32 (0)4 379 96 10
Fax: +32 (0)4 374 06 03
e-mail: be_info@elcometer.be
www.elcometer.be

FRANCE

Elcometer Sarl
97 Route de Chécý
45430 BOU

Tel: +33 (0)2 38 86 33 44
Fax: +33 (0)2 38 91 37 66
e-mail: fr_info@elcometer.fr
www.elcometer.fr

GERMANY

Elcometer Instruments GmbH
Ulmer Strasse 68
D-73431 Aalen

Tel: +49 (0)7361 52806 0
Fax: +49 (0)7361 52806 77
e-mail: de_info@elcometer.de
www.elcometer.de